

10/12/87 flaking in top quadrant
consolidated w/ PVA-AYAA, TOLUENE, 10%
Joan Borman SLA.

Keys replaced where necessary
backing boards secured w/ screws
reverse of painting vacuumed